

Material - ASTM F799 Alloy 2

Standard Specification for Cobalt-Based alloy

Group - Non-Ferrous Cobalt Alloys

Sub Group - ASTM F799 Alloy 2 Cobalt-Based alloy

Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
-	-	-	As-Cast or Annealing	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	1172 min.
-	-	-	Yield Strength in Mpa	827 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	12 min.
-	-	-	Hardness in HRC	35 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
R31538	UNS	USA	Casting
5832-12 Alloy 2	ISO	International	Casting
F1537 Alloy 2	ASTM	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.